

POREX® Virtek™ PTFE Materials

MD10

Parameters	Value	Unit of Measurement
BACTERIAL FILTRATION EFFICIENCY	>99.9%	ASTM F2101 ¹ (nominal)
WATER ENTRY PRESSURE (WEP)	Min 175, Typical 270	mbar
AIR FLOW	Min 70, Typical 107	l/hr/cm ² Δp 70mbar
THICKNESS	0.13	mm (nominal)

Additional Information

- Can be supplied in format of:
 - Rolls (8mm-330mm width) on 75mm core
 - Sheets
 - Discs

- Assembly suggestions:

- Ultrasonic welding
- Thermal welding
- Over-moulding
- Pressure Sensitive Adhesive
- Compression seal

- Sterilisation method:

- Steam/Autoclave (repeated use)
- EtO

- Raw material is compliant with:

- USP 28, NF 23, 2005, for USP Class VI Plastics at 70°C
- FDA 21CFR 177.1550
- PFOA Free, Compliant with (EC) No 1907/2006 REACH and Persistent Organic Pollutants (POP) EU 2019/1021



¹ ASTM F2101 was adapted to employ a more severe challenge. Test conditions and data available on request.

This standard sample is for evaluation of form, fit, and function to determine product specification requirements for custom products. Please reference the values in our data sheet for specification guidelines of standard products. In Vitro Diagnostic (IVD), medical-surgical and pharmaceutical samples are for investigational use only and subject to specific application, test condition and regulatory requirements.



Porex Corporation
500 Bohannon Road
Fairburn, GA 30213
USA

Porex Technologies GmbH
Strangenhäuschen 30
52070 Aachen
Germany

Porex Technologies Sdn Bhd
Lot PT 74, Jln Hulu Tinggi 26/6,
Sek. 26, Hicom Industrial Park,
40400 Shah Alam, Selangor, Malaysia

CON002429 Rev 5.00

info.porex.us@filtrationgroup.com
Tel: +1 770 964 1421
Fax: +1 770 969 0954

info.porex.europe@filtrationgroup.com
Tel: +49 241 9105250
Fax: +49 241 91052516

info.porex.asia@filtrationgroup.com
Tel: +603 51913308
Fax: +603 51923308